

Magnetic Sensor (3B)

- Magnetism
- Hall Effect
- AMR Effect
- GMR Effect

Copyright (c) 2009 Young W. Lim.

Permission is granted to copy, distribute and/or modify this document under the terms of the GNU Free Documentation License, Version 1.2 or any later version published by the Free Software Foundation; with no Invariant Sections, no Front-Cover Texts, and no Back-Cover Texts. A copy of the license is included in the section entitled "GNU Free Documentation License".

Please send corrections (or suggestions) to youngwlim@hotmail.com.

This document was produced by using OpenOffice and Octave.

Magnetism

Ferro-magnetic material

- **Permanent magnet**

Ferri-magnetic material


- **Below Curie Temp: like ferromagnets**
- **Above Curie Temp: like paramagnets**

Para-magnetic material

- **DC Josephson: $I > I_c$ then in the resistiv**

Hall Effect (1)


Transient State



Applied external magnetic field

- charges deflect
- charges are accumulated
- electrical potential (E_H) are created

As E_H increases, new (+) and (-) charges are repelled by those previously accumulated charges. (balancing effect)





Hall Effect (2)


The force F_e counteracts F_m .

- F_e : due to E_H
- F_m : due to external magnetic field B_z

Again charges travels straight,
but with the Hall angle θ .




Hall Effect (3)





Hall Effect - Geometric Factor (1)

$$f_H = \text{function}\left(\frac{l}{w}, \theta\right)$$



Hall Effect - Geometric Factor (2)




The force F_e counteracts F_m .

- F_e : due to E_H
- F_m : due to external magnetic field B_z

More charges are accumulated at the both ends until they repel other new charges.


Physical Magneto-resistance Effect

Ideal Case



Semiconductor


Real Case





- **Different Lorentz Force to each charge**
- **Different charges travel different paths**
- **The total length of paths is increased**
- **The resistance increases slightly**

Geometrical Magneto-resistance Effect (1)

Ideal Case




Real Cases




Metal Electrode Contact

Geometrical Magneto-resistance Effect (2)

Min R₁




B_z: Max R₁




$$\text{ratio } \frac{R}{R_0} = \frac{\max R_1}{\min R_1}$$

Min R₂



B_z: Max R₂



$$\text{ratio } \frac{R}{R_0} = \frac{\max R_2}{\min R_2}$$



Magnetic Anisotropy (1)


Magneto-crystalline Anisotropy

- **An intrinsic property of a ferri-magnet**
- **Magnetization curve along different crystal directions**


- **Easy direction**
- **Hard direction**
- **Intermediate direction**

Magnetic Anisotropy (2)

 **Easy direction**



Magnetization




Permalloy Resistor
: NiFe (ferri-magnet)



Permalloy Resistor (1)

 **Easy direction**



R_{\max} : small current

: parallel current direction



R_{\min} : large current


: perpendicular current direction



Permalloy Resistor (2)




Fix the direction of current



External Magnetic Field changes

- the magnetization direction of permalloy
- the resistance
- the current




H_{applied}

AMR Sensor (1)

The current direction is fixed


R_{\max} : small current

: parallel current direction



R_{\min} : large current

: perpendicular current direction





AMR Sensor (2)

How the current direction is fixed?


 Shortening Bars

Barber Pole Biasing
: the shortest path



Giant Magneto-resistance Effect


**Anti-parallel
Magnetic Layers**



High Interface Scattering

: R_{\max}

**Parallel
Magnetic Layers**



Low Interface Scattering

: R_{\min}


Magnetic Layer

Non-magnetic Conductor

Magnetic Layer

GMR Sensor

**Anti-parallel
Magnetic Layers**




High Interface Scattering

: R_{\max}

**External Magnetic
Field Change**



**Parallel
Magnetic Layers**



Low Interface Scattering

: R_{\min}

References

- [1] <http://en.wikipedia.org/>
- [2] Nam Ki Min, Sensor Electronics, Dong-il Press
- [3] <http://www.sensormag.com/> articles